



TOPSIDE PAINT

- Exceptionally easy one-part application
- Long lasting, durable polyurethane finish
- Provides superior gloss retention

Topside Paint

Woolsey® Topside Paint is a one-part polyurethane topside and deck enamel that features easy brushability. Its advanced ultraviolet filters enhance the superior gloss retention and durability of polyurethane. The result is a topside finish that's exceptionally easy to apply, producing a lasting gelcoat-like brilliance with minimum effort. It is economical, requires less effort, and is more forgiving than other finishes.

Woolsey Topside Paint is easy to clean, resists staining and has excellent abrasion resistance. Apply to fiberglass, wood, or previously painted surfaces on boats, RVs or other applications where an easy to apply, high gloss finish is desired.

TECHNICAL INFORMATION

VEHICLE TYPE: Oil modified polyurethane
FINISH: High gloss
SOLIDS BY WEIGHT: 62 ± 7%
COVERAGE: 150 ft²/qt.
VOC: 394 grams/liter (for white)
**Other colors will vary slightly*
FLASH POINT: >113°F (for white)
**Other colors will vary slightly*
APPLICATION METHOD: Brush, roller, airless or conventional spray
MAXIMUM ROLLER THICKNESS: 3/16"
NUMBER OF COATS: 2 minimum
WET FILM THICKNESS: 3 mils
DRY FILM THICKNESS: 1.5 mils
APPLICATION TEMP: 50°F Min / 90°F Max
THINNER/CLEANER: Mineral Spirits
DRY TIME: Minimum time in hours


	TO TOUCH	TO RECOAT
90°F	1-1/2	8
70°F	3	16
50°F	6	24

AVAILABLE IN THESE COLORS


Note: Color differences may occur between actual color chips shown.



BLACK
108



WHITE
175



SEMI-GLOSS WHITE
106



PLATINUM GRAY
111



APPLICATION INFORMATION: Woolsey Topside Paint may be applied by brush, roller, conventional or airless spray. For brush or roller application, apply without thinning, although in hot weather 5-10% mineral spirits may be added to maintain a wet edge. For best results on large, smooth surfaces, roll out using a short nap roller followed immediately by leveling off with the tip of a brush. Apply one, thin, even coat per day. After an overnight dry, lightly sand with 220 grit sandpaper and apply an additional coat. Applying two or more coats in one day or applying excessively heavy films greater than 4 wet mils will lead to insufficient through drying of the paint and will yield soft paint films. For conventional spray application thin 15-20%. For airless spray application thin up to 5%. Utilize a .011-.015-inch diameter tip for application. Do not apply Woolsey Topside Paint on extremely humid days 90°F+ RH or when rain is threatening. Do not apply in the late afternoon when working outdoors as the wet film may be adversely affected by dew. When working in cooler temperatures be sure the air and surface temperatures will remain at or above 50°F for at least 8 hours after application.

SURFACE PREPARATION: Coating performance, in general, is proportional to the degree of surface preparation. Follow recommendations carefully, avoiding shortcuts. Inadequate preparation of surfaces will virtually assure inadequate coating performance. Surface must be free of dirt, loose paint, rust, oil, grease, wax, soap and any other foreign matter. Remove mildew with household bleach instead of ammonia.

BARE WOOD: Sand surface smooth with 120 grit sandpaper, then solvent clean to remove residue. Fill all screw heads or small holes. Apply a coat of wood sealer to penetrate and seal the porous grain. Follow with one or two coats of Woolsey Topside Primer until an evenly smooth base condition is reached; sand each coat with 120 grit sandpaper and solvent clean. Proceed with the first finish coat of Woolsey Topside Paint. Bare wood that has been epoxied must be thoroughly scrubbed with an ammonia/water solution, then sanded with 120 grit sandpaper and solvent cleaned. Follow with a coat of Woolsey Topside Primer to smooth the surface and provide a uniform base. Sand well and solvent clean, then proceed with the first coat of Woolsey Topside Paint.

BARE STEEL: Surface must be cleaned to a bright finish by sandblasting or grinding; remove blast residue. Immediately apply one coat of Woolsey Metal Primer; allow to dry until tacky. If surface is rough, apply a coat of Woolsey Topside Primer; sand well and solvent clean. Repeat application as needed until a smooth, uniform base is reached. Proceed with the first coat of Woolsey Topside Paint.

BARE FIBERGLASS: The entire surface to be painted, regardless of age, must be thoroughly prepped to remove all traces of mold release agents and wax. Sand the gel coat with 120 grit sandpaper to a dull, frosty appearance, solvent clean to remove residue. If the surface is in excellent condition, proceed with the first finish coat of Woolsey Topside Paint. If the surface is rough or imperfections exist, it will have to be repaired. Fill all nicks and gouges; sand flush when hard, then solvent clean. Follow with a coat of Woolsey Topside Primer to smooth the surface and provide a uniform base; sand well and solvent clean. Proceed with the first finish coat of Woolsey Topside Paint.

PAINTED SURFACES: Clean and prep surface well. Remove mildew with household bleach. Never mix bleach and ammonia. If the old paint is an oil-based enamel or polyurethane, and is in good, sound condition, sand it thoroughly smooth with 150 grit sandpaper, solvent clean to remove residue, then proceed with the first coat of Woolsey Topside Paint.

If the old paint is a latex or water-based paint, or is in poor condition, remove it with a paint and varnish remover or by sanding. Proceed with instructions for the appropriate bare surface system.

ALUMINUM: Clean and prep the surface well. Remove oxidation and etch the surface with medium grit emery cloth; remove sanding residue. Apply one thin "wet" coat of Woolsey Metal Primer; allow to dry tacky. Proceed with one or two coats of Woolsey Topside Primer to smooth the surface and provide a uniform base. Sand well and solvent clean, then proceed with the first coat of Woolsey Topside Paint.