



EPOXY POOL PAINT



- High solids, high gloss finish
- Use for indoor or outdoor pools
- 3 to 5 years service life

Epoxy Pool Paint

Woolsey® Epoxy Pool Paint cures to a hard, tough and durable finish providing stain, chemical and abrasion resistance for protection of concrete, plaster and fiberglass swimming pools, spas and slides.

This product cures to a high gloss finish with excellent coverage rates, especially on previously painted epoxy surfaces. Because of their chemical cure, epoxies are the paints of choice for indoor and outdoor pools.

TECHNICAL INFORMATION

VEHICLE TYPE: Epoxy Polyamide
FINISH: High Gloss
COMPONENTS: 2
MIX RATIO: 2:1 by volume A:B
POT LIFE: 8 hours
SOLIDS BY VOLUME: 60 ± 3%
SOLIDS BY WEIGHT: 73 ± 2%
COVERAGE: 175-200 sq. ft./gal. on bare, sandblasted or rough surfaces. 400-500 sq. ft./gal kit on recoats
VOC: 340 g/l max. (as supplied)
FLASH POINT: >60°F (SETA)
APPLICATION METHOD: Brush, use no thicker than 3/8" mohair or lambskin roller, airless or conventional spray.
NUMBER OF COATS: 2 (Product is self-priming)
DRY FILM THICKNESS: Min 1.7 mils; 2.9 wet mils.
Max 2 mils; 3.3 wet mils.
APPLICATION TEMP: 50°F Min / 90°F Max
DRY TIME BETWEEN COATS: 16-20 hours. After 72 hours, must sand before applying 2nd coat.
DRY TIME: **Outdoor Pool:** 5-7 days to fill pool
Indoor Pool: 10-14 days to fill pool
To Recoat: 12-72 hours
THINNER: Xylene

AVAILABLE IN THESE COLORS

Note: Color differences may occur between actual color chips shown.



DAWN BLUE
909



WHITE
908



For compatibility purposes, the existing paint on previously painted surfaces of a pool or spa should be determined before painting. Aged plaster should be checked for integrity. Check for hollow or weak, crumbling plaster by using a ball-peen hammer or any other comparable method. Perform repairs to the plaster before painting.

APPLICATION SYSTEMS: Use no thicker than a 3/8" nap roller for solvent based paints. DO NOT use rollers with cardboard cores. Apply at the recommended coverage rate. Ideal air temperatures for application are between 50°F, no more the 90°F. Overnight curing temperatures must be at least 50°F or the paint will not cure properly causing an "oily" feel to the top of the paint. Do not paint when rain is imminent.

SURFACE PREPARATION: Coating performance, in general, is proportional to the degree of surface preparation. Follow recommendations carefully, avoiding shortcuts. Inadequate preparation of surfaces will virtually assure inadequate coating performance. Use tri-sodium phosphate (TSP), sulfamic or muriatic acid solution and high-pressure (3000 p.s.i.) minimum power washer. Scrub the entire pool surface with TSP solution to remove all dirt, oils and chalk. All surfaces should then be acid etched with 15-20% solution of sulfamic or muriatic acid to remove mineral deposits and to achieve a medium sandpaper grade finish on bare concrete or plaster surfaces. Neutralize/rinse with TSP and water. If surface is exceptionally hard, we recommend sanding with 60-80 grit sandpaper to create surface profile, prior to applying the first coat of Woolsey Epoxy Pool Paint. New concrete and plaster surfaces must be cured a minimum of 28 days prior to painting.

FOR PREVIOUSLY PAINTED EPOXY POOLS: You will need the following cleaning supplies: Tri-sodium phosphate (TSP) and muriatic or sulfamic acid solution; high pressure power washer with minimum 3000 p.s.i., turbo tip attachment, #80 grit sandpaper, a power sander, sanding block and a wire brush.

The existing epoxy must be cleaned with the TSP well, all residue removed, sand with 80 grit to create mechanical adhesion, remove all residue and then apply Woolsey Epoxy Pool Paint.

JOINT AND CRACK FILLER: Plaster or concrete surfaces should be tested for integrity and soundness. Power wash the surface to remove loose paint and dirt. Should any minor repairs need to be made, such as hydraulic cement patch or crack joint filling, do them at this time. Do not use silicone-based products, as paint adhesion will be adversely affected. For compatibility purposes, the existing paint on previously painted surfaces of a pool or spa should be determined before painting. Aged plaster should be checked for integrity. Check for hollow or weak/crumbling plaster by using a ball-peen hammer or any other comparable method. Perform repairs on the plaster before painting.

CONDENSATION TEST: After all cleaning is completed, allow the pool surface to dry. Average dry times vary regionally and are dependent upon the porosity of the surface. It is recommended to wait 5 dry sunny days then perform a condensation test to determine surface dryness.

- Tape 2'x2' pieces of transparent plastic to areas in the deep end wall, floor and several of the other areas of the pool.
- Wait about 4 hours to determine if condensation has formed underneath the plastic.
- If condensation is evident, the surface is not dry enough to paint.
- Remove the plastic and wait 24 hours to perform the test again and continue until no condensation forms. This ensures that the surface is dry enough to apply paint.

MIXING THE PAINT: Woolsey Epoxy Pool Paint is self-priming; no other type of primer is recommended or should be used.

1. Mechanically mix Part A for approximately 5 minutes
2. Mechanically mix Part B for approximately 5 minutes
3. Mechanically mix both Part A and Part B together for approximately 15 minutes.

Mixing with a stir stick is not recommended. Woolsey Epoxy Pool Paint has a pot life (use life) of 8 hours. Once mixed allow the material to stand at 65°F and above for 30 minutes. Allow to stand at 1 hour at temperatures 50°F—65°F to ensure chemical reaction before using. If material is used too soon after mixing or if pool is filled too soon after application yellowing or loss of gloss can occur. If more than one gallon kit is used at a time intermix several gallons together.