



# SYNTHETIC POOL PAINT



- *Self-priming, gloss finish*
- *Upgrade and restore previously painted synthetic or chlorinated rubber paints*
- *Excellent coverage*

## Synthetic Pool Paint

This product is a premium rubber coating formulated to provide excellent hiding, coverage and protection. It restores and upgrades previously painted chlorinated rubber and synthetic rubber surfaces, and is VOC Compliant in all 50 states.

This product allows the pool to be filled in as little as 5 days after the final application of paint outdoors. This product features a 4 year service life.

## TECHNICAL INFORMATION

**FINISH:** Gloss  
**SOLIDS BY VOLUME:** 43%  
**COVERAGE:** 300-400 ft<sup>2</sup>/gal on recoats.  
**VOC:** 325 grams/liter  
**APPLICATION METHOD:** Brush, roller, airless or conventional spray  
**MAXIMUM ROLLER THICKNESS:** 3/8"  
**NUMBER OF COATS:** 2 minimum  
**WET FILM THICKNESS:** 2.3 mils  
**DRY FILM THICKNESS:** 1 mil  
**APPLICATION TEMP:** 50°F Min / 90°F Max  
**DRY TIMES: OUTDOOR POOL:**  
5-7 days before filling  
**INDOOR POOL:**  
10 - 14 days before filling

**NOTE:** USE ADEQUATE VENTILATION

## AVAILABLE IN THESE COLORS

**Note:** Color differences may occur between actual color chips shown.



**DAWN BLUE**

963



**WHITE**

962



**COATING PERFORMANCE, IN GENERAL, IS PROPORTIONAL TO THE DEGREE OF SURFACE PREPARATION. FOLLOW ALL RECOMMENDATIONS VERY CAREFULLY, AVOIDING ANY SHORTCUTS.**

**COMPATIBILITY:** For compatibility purposes, the existing paint on previously painted surfaces of a pool should be determined before painting.

**SURFACE REPAIRS AND JOINT/CRACK FILLER:** Plaster or concrete surfaces should be tested for integrity and soundness. Aged plaster should be checked for integrity. Check for hollow or weak/crumbling plaster by using a ball-peen hammer or any other comparable method. Perform repairs before painting. Power wash to remove loose paint and dirt. Any minor repairs, such as patching with hydraulic cement or filling of cracks, should be done and allowed to cure prior to surface prep. We suggest using polyurethane sealant. Sealant must be top-coated before being submersed in chemically treated water.

**SURFACE PREPARATION:** Coating performance, in general, is proportional to the degree of surface preparation. Follow recommendations carefully, avoiding shortcuts. Inadequate preparation of surfaces will virtually assure inadequate coating performance. Use tri-sodium phosphate (TSP), sulfamic or muriatic acid solution and high-pressure (3500 PSI) minimum power washer. Scrub the entire pool surface with TSP solution to remove all dirt, oils and chalk. All surfaces should then be acid etched with 15-20% solution of sulfamic or muriatic acid to remove mineral deposits and to achieve a medium sandpaper grade finish on bare concrete or plaster surfaces. Neutralize/rinse with TSP and water. If surface is exceptionally hard, we recommend sanding with 60-80 grit sandpaper to create surface profile, prior to applying the first coat of Woolsey Synthetic Pool Paint. New concrete and plaster surfaces must be cured a minimum of 28 days prior to painting.

**APPLICATION:** Use no thicker than a 3/8" nap roller. DO NOT use rollers with cardboard cores. Apply at the recommended coverage rate. Ideal air temperatures for application are between 50°F and 90°F. Surface temperature should be at least 50°F, and no more than 90°F. Overnight drying temperatures MUST be at least 50°F. Do not paint when rain is imminent. Rain, moisture or excessively high humidity can cause blistering, color blushing and the finish could be adversely affected. If rain occurs during the drying process allow an extra day of dry time for each day of rain.

**MIXING THE PAINT:** This product is self priming; no other primer is recommended or should be used. Mechanically mix the paint to achieve uniform consistency and color. If more than one (1) gallon of paint is used at a time, box (intermix) several gallons together.

**SPRAY INFORMATION:** Airless: 2000-2500 PSI, Tip Size: .013 - .017 (0.33 – 0.43 mm)